

PCTFE

fluteck[™] C series



— SIZE LIST

Index

- Virgin PCTFE molded tubes
- Virgin PCTFE extruded and molded rods
- Virgin PCTFE molded sheets

Virgin PCTFE molded tubes

Metric sizes

O.D. (mm)	I.D. (mm)	O.D. (mm)	I.D. (mm)	O.D. (mm)	I.D. (mm)	O.D. (mm)	I.D. (mm)	O.D. (mm)	I.D. (mm)	O.D. (mm)	I.D. (mm)
70	35	160	130	220	155	265	220	340	300	525	495
	40	165	130		190		233		320	535	510
80	35		138	228	195	275	240	350	300	540	495
	50	170	125		160		215		310		510
85	35		135	230	190	280	233	360	320	570	525
	50	180	135		165		250		310	590	560
95	80		145	235	175	285	250		320	620	580
105	70		150		200		260	375	330	650	610
118	70		160	240	210	290	250		310		620
123	70	185	145		188		260	300	335	660	620
	85		155	245	205	320	240		345	685	650
132	105	195	135		200		250	285	340	710	680
133	85		150	250	210	330	270	390	355	750	720
	90	200	160		220		280	420	385	795	760
145	90		135	255	210	330	260	435	400	850	825
	100	205	150		215		270		410	900	860
148	110		180	210	330	330	280	460	425	940	910
153	110	205	160				280	485	450	980	930
160	125	210	180		215		300	510	470	1110	1070

Tubes length up to O.D. 650 mm: 150 mm, 300 mm - Special length on request

Tubes length over O.D. 650 mm: 100 mm - Special length on request

Tolerances according to corporate standard specifications: O.D: +2.0% - 0.0%. I.D: -2.0% + 0.0%. Length: +2.0% - 2.0%

Imperial sizes

O.D. (inch)	I.D. (inch)	O.D. (inch)	I.D. (inch)	O.D. (inch)	I.D. (inch)	O.D. (inch)	I.D. (inch)	O.D. (inch)	I.D. (inch)	O.D. (inch)	I.D. (inch)
2.750"	1.500"	7.125"	5.875"	9.250"	8.250"	11.250"	9.875"	14.125"	12.500"	22.500"	20.750"
	1.375"		5.750"		7.875"		10.125"		12.125"	23.250"	20.000"
3.125"	1.875"	7.250"	5.375"	9.500"	8.125"	11.375"	9.750"	14.750"	13.500"	24.375"	22.750"
	1.375"		6.000"		8.625"		11.125"		13.125"	25.625"	24.375"
3.750"	3.150"	7.750"	5.625"	9.625"	9.625"	11.875"	10.625"	15.125"	13.375"		24.000"
3.375"	2.000"		6.375"		7.875"		9.875"	15.375"	14.000"	25.875"	24.250"
4.125"	2.750"	7.875"	6.000"	9.875"	8.500"	12.625"	11.000"	16.500"	15.125"	27.000"	25.625"
4.875"	3.375"		7.125"		8.250"		10.625"	17.125"	16.125"	28.000"	26.750"
5.250"	3.625"	8.125"	5.875"	10.000"	9.750"	13.000"	11.750"		15.750"	29.500"	28.250"
5.750"	4.000"		5.375"		8.500"		11.000"	18.125"	16.750"	31.250"	29.875"
6.000"	4.375"	8.125"	6.375"	10.375"	9.125"	13.375"	11.750"	19.125"	17.750"	33.500"	32.500"
6.375"	5.125"	8.250"	7.000"		8.625"	13.750"	12.500"	20.125"	18.500"	35.375"	33.750"
	5.000"	8.625"	7.625"	10.750"	9.375"		12.125"	20.625"	20.125"	37.000"	35.750"
6.500"	5.125"		7.375"	11.000"	9.750"	14.125"	11.750"	21.250"	20.000"	38.625"	26.625"
6.750"	5.375"	9.000"	7.500"		8.500"		12.875"		19.500"	43.750"	42.125"
	5.000"	9.125"	6.625"	11.250"	10.250"						

Tubes length up to O.D. 25.875": 4" - 6" - special length on request

Tubes length over O.D. 25.875": 4.0" - special length on request

Tolerances according to corporate standard specifications: O.D: +2.0% - .0%. I.D: - 2.0% +.0%. Length: +2.0% - 2.0%

Virgin PCTFE extruded and molded rods

Metric sizes

O.D. (mm)										Length (mm)
6	8	9	10	11	12	13	15	16	18	1000 2000 3000
20	22	23	25	28	30	35	40	45		1000
45	50	55								500
60	70	80	90	100						200

Virgin PCTFE molded sheets

Metric sizes

Thickness (mm)	300x300 (mm)	500x500 (mm)
5	•	on request
8	•	•
10	•	•
12	•	•
15	•	•
20	•	•
25	•	on request
30	•	on request
35	on request	on request
40	on request	on request
45	on request	on request
50	on request	on request

Technical data sheet

	Properties	Method	Units	fluteck™ P1000 Virgin PTFE Standard Grade	fluteck™ P1050 Modified PTFE Standard Grade	fluteck™ P1500 Virgin PTFE Premium Grade	fluteck™ P1550 Modified PTFE Premium Grade
Physical	Specific Gravity	ASTM D792	g/cm ³	2.13 - 2.19	2.13 - 2.18	2.13 - 2.19	2.13 - 2.18
	Water absorption - 24 hours	ASTM D570	%	0.01	0.01	0.01	0.01
Mechanical	Elongation at break	ASTM D4894	%	≥ 200	≥ 400	≥ 280	≥ 450
	Tensile strength	ASTM D4894	MPa	≥ 20	≥ 28	≥ 25	≥ 30
	Shore D hardness	ASTM D2240	Shore D	≥ 54	≥ 54	≥ 54	≥ 54
	Ball hardness	ASTM D785	MPa	≥ 23	≥ 23	≥ 23	≥ 23
	Compression strength at 1% deformation	ASTM D695	MPa	≥ 4	≥ 4	≥ 4	≥ 4
	Deformation under load (140 kg/cm ² for 24h at 23°C)	ASTM D621	%	10 - 13	9 - 12	10 - 13	9 - 12
	Permanent deformation (after 24h at 23°C)	ASTM D621	%	6 - 7.5	4.5 - 6	6 - 7.5	4.5 - 6
	Coefficient of static friction	ASTM D1894	-	0.08 - 0.10	0.08 - 0.10	0.08 - 0.10	0.08 - 0.10
	Coefficient of dynamic friction	ASTM D1894	-	0.06 - 0.08	0.06 - 0.08	0.06 - 0.08	0.06 - 0.08
	Wear factor K	ASTM D3702	-	2.9	2.9	2.9	2.9
Thermal	Wear coefficient		$\frac{\text{cm}^3 \text{ min}}{\text{kg m h}} \cdot 10^{-8}$	20000 - 25000	20000 - 25000	20000 - 25000	20000 - 25000
	Thermal conductivity	ASTM C177	W/m·K	0.34	0.24	0.34	0.24
	Flammability	UL94	-	V - 0	V - 0	V - 0	V - 0

The information in this technical data sheet have been collected from reliable statistic series.

All informations are intended only as general guide lines for use at user discretion.

Fluoroseals does not guarantee any specific result and do not assume any liability in connection with the use of the product.

Technical data sheets

	Properties	Method	Units	fluteck™ P1500 PTFE	fluteck™ K300 PEEK	fluteck™ C100 PCTFE	fluteck™ C200 ECTFE	fluteck™ F100 PFA	fluteck™ E200 FEP	fluteck™ E400 ETFE
Physical	Specific Gravity	ASTM D792	g/cm³	2.130 - 2.190	1.30 - 1.32	2.10 - 2.16	1.62 - 1.68	2.13 - 2.18	2.12 - 2.16	1.72
	Water absorption - 24 hours	ASTM D570	%	0.01	0.1	< 0.01	< 0.10	< 0.03	< 0.01	< 0.01
	Mold shrinkage - along the flow	ASTM D955	%	1.50 - 2.00	1 - 1.5	1.50 - 2.00	2.5	4 - 5	3 - 5	2 - 3.5
Mechanical	Elongation at break	ASTM D638	%	≥ 280	≥ 10	40 - 150	≥ 200	≥ 250	≥ 300	≥ 200
	Tensile strength (23°C)	ASTM D638	MPa	> 25	≥ 95	31 - 45	40	> 23	25	> 35
	Flexural strength, at break	ASTM D790	MPa	no break	≥ 140	40 - 50	40	no break	no break	38
	Flexural modulus	ASTM D790	MPa	600 - 700	3800	1200	1500	500	600	1000
	Shore D hardness	ASTM D785	-	D54	D80	D80	D75	D60	D56	D65
	IZOD notched impact (23°C)	ASTM D256	J/m	161	≥ 85	150	no break	no break	no break	no break
	Coefficient of dynamic friction (vs. itself)	ASTM D1894	-	0.06 - 0.08	≤ 0.2	0.35	0.2	0.21	0.3	0.23
Thermal	Melting temperature (°F/°C)	ASTM D3418	(°F/°C)	621/327	644/340	410/210	432/222	582/305	500/260	518/270
	Max operating temperature (°F/°C)	-	(°F/°C)	500/260	572/300	302/150	302/150	500/260	400/204	302/150
	Flammability rating	UL 94	-	V - 0	V - 0	V - 0	V - 0	V - 0	V - 0	V - 0
	Heat deflection tem- perature (0.45 MPa)	ASTM D648	(°F/°C)	132/55	315/157	176/80	194/90	163/73	158/70	176/80
	Min. short term service temperature	-	(°F/°C)	- 320/ - 196	- 148/ - 100	- 328/ - 200	- 148/ - 100	- 328/ - 200	- 328/ - 200	- 148/ - 100
Electrical	Dielectric constant, at 1KHz	ASTM D150	-	2.1	3.2	2.3	2.48	2	2.15	2.6
	Dielectric strength (23°C, 1.0 mm)	ASTM D149	KV/mm	≥ 30	≥ 22	32	30	33	35	30
	Dissipation factor, at 1KHz	ASTM D150	-	0.0001 - 0.0003	0.003	0.0012	0.0012	0.00082	0.00094	0.015
	Arc resistance (sec)	ASTM D495	sec	300	40	> 320	> 120	> 180	> 300	> 100
	Volume resistivity, at 50% RH	ASTM D257	(ohm*cm)	> 10 ¹⁸	> 10 ¹⁷	> 10 ¹⁷	> 10 ¹⁷	> 10 ¹⁸	> 10 ¹⁸	> 10 ¹⁷

The information in this technical data sheet have been collected from reliable statistic series.

All informations are intended only as general guide lines for use at user discretion.

Fluorseals does not guarantee any specific result and do not assume any liability in connection with the use of the product.

